

Material Safety Data Sheet

Revision Date: 25.10.2005

(91/155/EWG)

Page 1 of 3

2010-22-13

1. Chemical product and company identification

Product name:

Soleil

Supplier:

DMG, Dental-Material Gesellschaft mbH
D 22531 Hamburg, telephone : (+49) 040 - 84 00 60
Emergency contact: Infotrac-(800)535-5053

2. Composition / Information on ingredients

Common chemical name / Generic name:

Preparation of acrylic resin, glass powder and silica.
Contains urethane dimethacrylate, aliphatic dimethacrylate, aromatic dimethacrylate.

3. Hazards Identification

None, if handled according to directions.
Irritating to eyes, respiratory system and skin.

4. First-aid measures

In case of inhalation: In case of prolonged exposure take patient to open air.
In case of skin contact: Wash with soap and water.
In case of eye contact : Rinse with plenty of water, consult a physician.
In case of ingestion: Immediately seek medical advice.

5. Fire-fighting measures

Extinguishing media: Powder, sand, foam, carbon dioxide, water spray.
Not suitable extinguishing media: direct jet of water

6. Accidental release measures

Personal precautions: Use only in well-ventilated areas.
Environmental precautions: Do not empty into drains.
Methods for cleaning up: Take up mechanically.

7. Handling and storage

Handling:

Technical measures: Keep container tightly closed.
Safe handling advice: Wear suitable gloves. Avoid contact with eyes.

Storage:

Technical measures: Keep container in a well-ventilated place.
Storage conditions: Keep container tightly closed. Keep in a dark, cool place.
Recommended packaging material: Container of solvent-stable plastics.

Material Safety Data Sheet

Revision date: 25.10.2005

Trade name: Luxatemp-Inlay

Page 2 of 3

2010-22-13

8. Exposure controls/personal protection

Engineering measures: Use only in well-ventilated areas.

Personal protective equipment:

Respiratory protection: Do not breathe vapour.

Hand and skin protection: Rubber gloves.

Eye protection: Goggles.

Hygiene measures: When using do not eat or drink.

9. Physical und chemical properties

Appearance: Slightly yellowish paste

Odour: esterlike, weak

pH-value: not applicable

Changes in physical state:

Decomposition temperature: > ca. 200 °C

Flashpoint: > 150 °C

Explosion properties: not established

Vapour pressure: < 1 mbar / 20 °C

Rel. vapour density: > 1

Density: ca. 1.8 g/cm³

Solubility in water: ca. 1 g/l / 20 °C

10. Stability and reactivity

Thermal decomposition: at ca. 200 °C

No decomposition, if handled according to directions.

Hazardous reactions: None, if handled and stored according to directions.

Conditions to avoid: Heat, light.

Materials to avoid: Free radicals, reducing agents, heavy metal ions.

Hazardous decomposition products: In case of fire acrid acrylic fumes.

Cures on exposure to visible or UV-light.

11. Toxicological information

Acute oral toxicity: LD₅₀ (Ratte) > 5000 mg/kg

Irritation of skin : Irritating on prolonged exposure.

Irritation of eye: Irritating on prolonged exposure.

Specific effects: Allergic reactions to methacrylates are possible.

12. Ecological information

Do not discharge into drains or the environment.

Persistence und degradability: No data available for the preparation.

13. Disposal considerations

Waste from residues: Use proper landfill disposal or incineration in accordance with local, state and federal regulations.

Material Safety Data Sheet

Revision date: 25.10.2005

Trade name: Luxatemp-Inlay

Page 3 of 3

2010-22-13

14. Transport information

Additional information: Not dangerous cargo.

15. Regulatory information

Labelling according international regulations: Xi, Irritant. Contains methacrylic ester.

Symbols of danger: St Andrew's cross.

R-Phrases: 36/37/38

Irritating to eyes, respiratory system and skin.

S-Phrases: 26 - 28

In case of contact with eyes rinse immediately with plenty of water and seek medical advice.

After contact with skin wash immediately with plenty of water and soap.

16. Other information

None.

The data given here is based on current knowledge and experience. The data does not signify any warranty with regard to the product's properties.